


# LIONOL BLUE ESP-S



Chemical structure

<b>Chemical Group :</b>	Phthalocyanine
<b>Colour Index :</b>	PB15:6
<b>C.I. Number :</b>	74160
<b>CAS Number :</b>	147-14-8
<b>EC Number :</b>	205-685-1

## Registration

MITI (Japan)	5-3299
TSCA (USA)	Registered

## Application

Automotive solvent	◎
Automotive water	◎
Industrial solvent	◎
Decorative solvent	◎
Decorative water	○
Powder coatings	

◎ Recommended      ○ Suitable

Note : The information herein and materials supplied to user is based on our general experience and where applicable, on the results of tests of typical manufacture. However, because of many factors which are outside our knowledge and control which can affect the use of these products, we decline liability for any injury, loss or damage resulting from reliance upon such information.

## Colour Chart



## Key Properties

An epsilon form phthalocyanine blue pigment with a very bright reddish shade, high colour strength and excellent rheological properties.

## Physical Properties

Bulk density (Kg/l)	0.24
Specific surface area (m <sup>2</sup> /g)	51

## **Fastness Properties**

### Chemical Resistance

Water	5
Xylene	5
Ethanol	5
Ethyl Acetate	5
Acid (HCl 2%)	5
Mineral Spirit	5
Alkali (NaOH 2%)	5

resistance to solvent, acid & alkali: 1 to 5, 5 = Excellent

### Light Fastness

Full shade	8
Reduced -1/10TiO <sub>2</sub>	7

assessment according to the Wool Scale (1-8)

### Weatherability

Open Air	Solid	Full	dE=1.8
Florida		1/10TiO <sub>2</sub>	dE=7.6
2 years	Metallics	3/1Al	dE=5.9
		1/9Al	dE=6.6

### Heat Stability

10' - 150 °C	5
10' - 210 °C	5

assessment according to the Gray Scale (1-5)

TOYOCOLOR CO., LTD.

Kyobashi EDOGRAND Bldg., 2-1, Kyobashi 2-chome, Chuo-ku, Tokyo, 104-8381  
JAPAN Tel +81 3 3272 3443 Fax +81 3 3272 3447 www.toyo-color.com

**TOYO**COLOR

For a Vibrant World

TOYO IN < GROUP