


LIONOL GREEN 8930



Chemical structure

Colour Chart



Key Properties

A Pigment Green 7 type pigment with high colour strength and good dispersibility.

Chemical Group : Phthalocyanine

Colour Index : PG7

C.I. Number : 74260

CAS Number : 1328-53-6

EC Number : 215-524-7

Physical Properties

Bulk density (Kg/l)	0.16
Specific surface area (m ² /g)	76

Registration

MITI (Japan)	5-3315
TSCA (USA)	Registered

Application

Rubber	◎
PVC	◎
LDPE	◎
HDPE / PP	◎
PS / PC / ABS	◎
Fiber	○

◎ Recommended ○ Suitable

Fastness Properties

Chemical Resistance

Water	5
Xylene	5
Ethanol	5
Ethyl Acetate	5
Mineral Spirit	5
Acid (HCl 2%)	5
Alkali (NaOH 2%)	5

Resistance to Solvent: 1 to 5, 5 = Excellent

Acid & Alkali Resistance: 1 to 5, 5 = Excellent

Light Fastness

Full shade	8
Reduced -1/10TiO ₂	8

assessment according to the Wool Scale (1-8)

Heat Resistance

300 °C

Note : The information herein and materials supplied to user is based on our general experience and where applicable, on the results of tests of typical manufacture. However, because of many factors which are outside our knowledge and control which can affect the use of these products, we decline liability for any injury, loss or damage resulting from reliance upon such information.

TOYOCOLOR CO., LTD.

Kyobashi EDOGRAND Bldg., 2-1, Kyobashi 2-chome, Chuo-ku, Tokyo, 104-8381
JAPAN Tel +81 3 3272 3443 Fax +81 3 3272 3447 www.toyo-color.com

TOYOCOLOR

For a Vibrant World

TOYOINKGROUP